

ENGINEERED COATINGS

GENERAL MOTORS COATINGS

SPECIFICATION	CODE/SUFFIX	DESCRIPTION	SALT SPRAY HRS.
GM 4277M	A-G	Mn Phosphate	--
GM 4345M	Varies	Zinc Plating	
GM 4435M	Code G	Zn Phosphate	72
GM 4435M	Code E	Zn Phosphate	24
GM 4435M	Code D	Zn Phosphate	
GM 4435M	Code B	Zn Phosphate	72
GM 4435M	Code A	Zn Phosphate	72
GM 6035M		Zn Phosphate	96
GM 6046M		Xylan 5230	Variable
GM 6047M		Electro Polyseal II	168
GM 6047M	G	Electro Polyseal III	168
GM 6111M		Magni 505 Dorritone	400
GM 6138M		E-Coat, Electroplate	
GM 6173M		Geomet	480
GM 6174M		Black Organic	168
GM 6280M		Tin / Zinc plating	
GM 7111M		Magni 511 (Dorriflake)	240
GM 7112M		Magni 512 (Dorrimate)	240
GM 7113M		Magni 560 (Topcoat)	400
GM 7114M		Magni 565	480
GM 7153M		Electroplate plus black coat	120/240
GME00255	A-F	Magni 590 / 591	Variable
GMW14100		Magni 511 (Dorriflake)	240
GMW14C-PT		Magni 590 or Geomet	480
GMW15821	A,D,G	Mn Phosphate	Variable
GMW3044	Varies	Zinc Plating	
GMW3179	A,D,G	Zn Phosphate	Variable
GMW3359	A,B,C	Magni 565 or Geomet	Variable
GMW4205		Magni 577	480
GMW4207		Zinc plate with topcoat	400
GMW4700		Tin / Zinc plating	

FORD MOTOR COMPANY WORLDWIDE

SPECIFICATION	SUFFIX	PROCESS OR TRADENAME	SALT SPRAY HRS.
WSD-M21P10-B1	(S302)	Electro Polyseal (No Oil)	72
WSD-M21P10-B2	(S303)	Black Organic	120
WSD-M21P10-B3	(S306)	Xylan 5230	240
WSD-M21P11-B2	(S307)	Magni 511 (Dorriflake Black)	480
WSD-M21P11-B4	(S412)	Magni 512 (Dorrimate)	480
WSD-M21P11-B5	(S410)	Magni 511 (Dorriflake)	120
WSD-M21P11-B6	(S411)	Magni 512 (Dorrimate)	120
WSD-M21P11-B8	(S426)	Magni 555 (Dorritech)	1000

WSD-M21P13-A3	(S301)	Dacromet	500
WSD-M21P19-A24	(S424)	Electro Polyseal II + Sealcoat	120
WSD-M21P19-A30	(S430)	Zn Phosphate + Oil	--
WSA-M21P26-A2	(S427)	Magni 550 (Dorrtech)	1000
WSS-M21P28-A2	(S436)	Texacote 452	24
WSS-M21P37-A1	(S439)	Magni 565	840
WSS-M21P37-A2	(S441)	Magni 511 (Dorrflake)	240
WSS-M21P37-A3		Magni 515	840
WSS-M21P39-A1,A2,A3	(S438)	Geomet	720/480
WSS-M21P40-A1	(S440)	Magni 560 (Topcoat)	840
WSS-M21P41-A, A2		Electro Polyseal II & III	120/240
WSS-M21P44-A3		Electro Polyseal V (Topcoat)	960
WSS-M21P49-A1	(S447)	Geomet 500	480
WSS-M21P49-A2	(S448)	Geomet 500	960
WSS-M21P49-A3 (Black)		Geomet 500	1008

FORD MOTOR COMPANY NAAO

SPECIFICATION	CODE/SUFFIX	DESCRIPTION	SALT SPRAY HRS.
S58	(S58)	Zn Phosphate + Dry Oil	48
ESB-M3P4-A		Zn Phosphate	72
ESB-M3P5-A		Zn Phosphate	96
ESF-M3P6-A		Zn Phosphate	24
ESF-M3P7-A		Zn Phosphate	96
ESF-M3P9-A		Zn Phosphate	--
ESF-M3P10-A		Zn Phosphate	48
ESS-M3P20-A		Zn Phosphate	72
ESA-M7C69-A	(S2)	Aqua-Phos	240
ESA-M7C69-A2	(S56)	Clear Aqua-Phos	240
ESA-M7C69-A3	(S59)	FM Aqua-Phos	240
ESB-M21P1-A	(S60)	Black Organic	168
ESF-M21P6-A	(S53B)	Electro Polyseal II	240

CHRYSLER GROUP, LLC

SPECIFICATION	CODE/SUFFIX	PROCESS OR TRADENAME	SALT SPRAY HRS.
PS-80		Zn Phosphate	72
PS-4764		Zn Phosphate	72
PS-8890 (Methods A,B)		MN Phosphate	--
PS-5873		Geomet	720
PS-7001		Xylan 5230	240
PS-7626		Magni 511 (Dorrflake)	400
PS-7902 (A, B,C)		Electro Polyseal II or III	240
PS-9295		Magni 550 or 510 (Topcoats)	720
PS-9666		Geomet	480
PS-10378 (Types A, B, C)		Magni 565, 575, 577	720
PS-10633		Magni 565 or Geomet	720
PS-11036		Magni 594 or Geomet	480
DBL 9440.40 (Silver)		Magni 594 / Geomet	720
DBL 9440.50 (Black)		Magni 591 / Geomet	240

DELPHI AUTOMOTIVE

SPECIFICATION	CODE/SUFFIX	PROCESS OR TRADENAME	SALT SPRAY HRS.
DX550041		Magni 511(Dorrflake)	240
DX550077		Black Organic	168